

## OK 61.30

Extra low carbon stainless steel electrode for welding steels of the 19 Cr 10 Ni-type. Also suitable for welding stabilized stainless steels of similar composition, except when the full creep resistance of the base material is to be met.

Specifications	
<b>Classifications</b>	EN ISO 3581-A : E 19 9 L R 1 2 SFA/AWS A5.4 : E308L-17 CSA W48 : E308L-17 Werkstoffnummer : 1.4316
<b>Approvals</b>	ABS : Stainless CE : EN 13479 CWB : E308L-17 DB : 30.039.02 DNV-GL : VL 308 L NAKS/HAKC : 2.0-4.0 mm Sepro : UNA 272580 VdTÜV : 00792
<b>Welding Current</b>	DC+, AC
<b>Ferrite Content</b>	FN 3-10
<b>Alloy Type</b>	Austenitic CrNi
<b>Coating Type</b>	Acid Rutile

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
<b>ISO</b>			
As Welded	430 MPa	580 MPa	45 %

Typical Charpy V-Notch Properties		
Condition	Testing Temperature	Impact Value
<b>ISO</b>		
As Welded	20 °C	70 J
As Welded	-60 °C	49 J

Typical Weld Metal Analysis %						
C	Mn	Si	Ni	Cr	N	Ferrite FN
0.03	0.7	0.9	10.0	19.3	0.09	5

Deposition Data						
Diameter	Current	Voltage	Efficiency (%)	Number of electrodes/kg weld metal	Fusion time per electrode at 90% I max	Deposition Rate
1.6 x 300.0 mm	35-45 A	27 V	55 %	240	24 sec	0.6 kg/h
2.0 x 300.0 mm	35-65 A	29 V	55 %	160	29 sec	0.8 kg/h
2.5 x 300.0 mm	50-90 A	31 V	55 %	99	36 sec	1.1 kg/h
3.2 x 350.0 mm	70-130 A	31 V	60 %	49	54 sec	1.4 kg/h
4.0 x 350.0 mm	90-180 A	32 V	60 %	33	60 sec	2.0 kg/h
5.0 x 350.0 mm	140-250 A	33 V	60 %	20	60 sec	3.0 kg/h